



DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
P.O. BOX 4004
BURLINGTON, NORTH CAROLINA 27215
PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

April 9, 2008

Mr. David Conine
SAFETY COMPONENTS FABRIC TECHNOLOGIES, INC.
P.O. Box 567
Greenville, SC 29602-0567

Reference: Flammability Test Report
Lab Identification No. 6021
Invoice No. 18447 (Attached)

Dear Mr. Conine:

One (1) fabric sample, identified as 29355 - BLACK - LOT # 3002541, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The results are as follows:

<u>Specimen Number</u>	<u>After Flame Time (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	3.9	4.6
2	0.0	0.0	3.7	4.1
3	0.0	0.0	4.2	4.2
4	0.0	0.0	4.1	4.4
5	0.0	0.0	4.0	4.4
Avg.	0.0	0.0		


The sample submitted, in its original state, **meets** the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
Attachment



DIVERSIFIED
TESTING LABORATORIES, INC.

“We Test Per Your Request”

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

April 9, 2008

Mr. David Conine
 SAFETY COMPONENTS FABRIC TECHNOLOGIES, INC.
 P.O. Box 567
 Greenville, SC 29602-0567

Reference: Flammability Test Report
 Lab Identification No. 6021
 Invoice No. 18447 (Attached)

Dear Mr. Conine:

One (1) fabric sample, identified as 29355 - BLACK - LOT # 3002541, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The sample was tested after 72 hours of leaching. The results are as follows:

<u>Specimen Number</u>	<u>After Flame Time (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	5.1	4.7
2	0.0	0.0	4.6	4.8
3	0.0	0.0	4.2	4.2
4	0.0	0.0	4.4	4.0
5	0.0	0.0	4.4	4.0
Avg.	0.0	0.0		

The sample submitted, when tested after 72 hours of leaching, meets the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
 Attachment



DIVERSIFIED

TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

April 9, 2008

Mr. David Conine
 SAFETY COMPONENTS FABRIC TECHNOLOGIES, INC.
 P.O. Box 567
 Greenville, SC 29602-0567

Reference: Flammability Test Report
 Lab Identification No. 6021
 Invoice No. 18447 (Attached)

Dear Mr. Conine:

One (1) fabric sample, identified as 29355 - BLACK - LOT # 3002541, was received and tested in accordance with the California Administrative Code Title 19--Public Safety, Section 1237. Flame Resistance, Small Scale Test. The sample was tested after 100 hours of accelerated weathering. The results are as follows:

<u>Specimen Number</u>	<u>After Flame Time (sec)</u>		<u>Char Length (in)</u>	
	<u>Length</u>	<u>Width</u>	<u>Length</u>	<u>Width</u>
1	0.0	0.0	4.5	5.1
2	0.0	0.0	4.1	4.7
3	0.0	0.0	4.4	4.7
4	0.0	0.0	4.9	4.2
5	<u>0.0</u>	<u>0.0</u>	5.2	4.6
Avg.	0.0	0.0		

The sample submitted, when tested after 100 hours accelerated weathering, meets the minimum requirements of the above standard. The char length may not exceed 6.0 inches for any individual specimen and the average afterflame time may not exceed 4.0 seconds in the length or width directions.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr
 Attachment